

PRODUCT DATA SHEET

Sika MonoTop®-612 N

POLYMER MODIFIED HIGH STRENGTH, HIGH BUILD CONCRETE REPAIR MORTAR

DESCRIPTION

Sika® MonoTop-612 N is a cement-based, one component low permeability concrete repair mortar, containing silica fume and polymer, meeting the requirements of Class R4 of EN 1504-3.

USES

- For repairing high strength concrete >45MPa
- High Build repairs horizontal, vertical and overhead
- For exterior and interior use
- New and old concrete repairs
- Marine repairs
- Trafficable repair applications

CHARACTERISTICS / ADVANTAGES

- Compatible with Sika® FerroGard® corrosion inhibitors
- Compatible with Sika® FerroGard® Sacrificial Anode System
- High build up to 100mm in one application*
- Low shrinkage
- High workability
- Very high resistivity mortar for durable new work concrete repairs
- AS/AZS 4020:2018 Approved for Potable/ drinking water contact
- Sulphate resistant in marine

APPROVALS / CERTIFICATES

- AS 4020:2018 potable water approved
- Qld Roads (TMR) Section 5. Registered and Conforming Products. Part 5.34 Repair Mortars
- RTA Rapid Mortar Bar Test RTA T363 - Alkali Reactive Particles <0.10% (Non-Reactive).

PRODUCT INFORMATION

Composition	Portland cement, polymer redispersable powder, selected aggregates and additives
Packaging	20 kg bag
Shelf life	12 months from date of manufacture
Storage conditions	Product must be stored in dry controlled conditions
Appearance and colour	Grey powder
Maximum grain size	D _{max} : 2.0 mm

TECHNICAL INFORMATION

Compressive strength	1 day	~ 18 MPa	(AS 1478.2:2005)
	7 days	~ 50 MPa	
	28 days	~ 70 MPa	
<i>Material and curing conditions at 23 °C / 50% r.h Above results based on 50mm x 50mm cubes @ 2.8 litres water per 20kg bag</i>			
Modulus of elasticity in compression	~ 25 GPa @ 28 days		(AS 1012.17)
Tensile strength in flexure	1 day	~ 4 MPa	(ASTM C 348)
	7 days	~ 8 MPa	
	28 days	~ 9 MPa	
Splitting tensile strength	28 days	~ 5.0 MPa	(AS 1012.10)
Tensile adhesion strength	> 2.0 MPa		(EN 1542)
Shrinkage	7 days	~ 250 microstrains	(AS 2350.13)
	28 days	~ 650 microstrains	
Restrained shrinkage / expansion	≥ 2.0 MPa @ 28 days		(EN 12617-4)
Electrical resistivity	7 days	~ 33,000 Ω.cm	(FM5-578) 50mm Probe Spacing
	28 days	~ 139,000 Ω.cm	
	56 days	~ 171,000 Ω.cm	
	90 days	~ 211,000 Ω.cm	
Capillary absorption	3.2 x 10 ⁻⁴ (mm/Vs)		(ASTM C 1585)
Chloride ion diffusion resistance	1.15 E-12 (m ² /s)		(NT443)

SYSTEM INFORMATION

System structure

Sika MonoTop®-612 N is part of the range of Sika mortars complying with the relevant part of European Standard EN 1504 and comprising of:

Bonding Primer / Reinforcement

Corrosion Protection

Sika Monotop® - 910 N	Normal Use
SikaTop® Armatec® 110 Epocem®	Demanding requirements

Repair Mortar

Sika Monotop® - 612 N	Class R4 concrete repair hand and machine applied
-----------------------	---

Levelling Mortar

Sika Monotop® - 723 N	Normal Use
Sikagard® - 720 Epocem®	Demanding requirements

APPLICATION INFORMATION

Mixing ratio	2.8 to 3.0 litres of water for 20 kg powder
Consumption	This depends on the substrate roughness and thickness of layer applied. As a guide, ~ 19.0 kg of powder per cm thick per m ²
Yield	20 kg of powder yields approximately 10.9 litres of mortar
Layer thickness	min. 5 mm / max. 100 mm
Ambient air temperature	+5 °C minimum; +30 °C maximum
Substrate temperature	+5 °C minimum; +30 °C maximum

Pot Life	~ 35 minutes at +23°C	
Initial set time	~ 2.0 hours	(AS 2350.4)
Final set time	~ 5.0 hours	(AS 2350.4)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Refer to the Method Statement for Concrete Repair using Sika MonoTop® system for more information regarding substrate preparation or refer to the recommendations provided in EN 1504-10
- Avoid application in direct sun and/or strong wind.
- Do not add water over recommended dosage.
- Apply only to sound, prepared substrate.
- Do not add additional water during the surface finishing as this will cause discolouration and cracking.
- Protect freshly applied material from freezing.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete:

The concrete shall be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.

Steel Reinforcement:

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed. Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to Sa 2 (ISO 8501-1) Reference shall be made to EN1504-10 for specific requirements.

MIXING

Sika MonoTop®-612 N can be mixed with a low speed (< 500 rpm) hand drill mixer or for machine application, using a force action mixer 2 to 3 bags or more at once depending the type and size of mixer. In small quantity, Sika MonoTop®-612 N can also be manually mixed. Pour the recommended water in a suitable mixing container. While stirring slowly, add the powder to the water and mix thoroughly at least for 3 minutes to the required consistency.

APPLICATION

Bonding Primer:

On a well prepared and roughened substrate a bonding primer is generally not required for this product. When a bonding primer is required, refer to the System Information above for compatible Sika products and refer to the relevant Product Data Sheet for instructions. All small amount of Sika MonoTop®-612 N can also be mixed slightly wetter than normal and used as a scratch coat to promote adhesion of the repair mortar to the substrate. Any bonding primer shall be applied on a pre-wet substrate in saturated surface dry (SSD) condition and subsequent application of the repair mortar shall be applied wet on wet with the bonding primer.

Reinforcement Corrosion Protection:

Where a reinforcement coating is required the application of a repair mortar shall be applied wet on dry with the reinforcement corrosion protection. Refer to the System Information above for compatible Sika products and refer to the relevant Product Data Sheet for more detailed information about the reinforcement corrosion product. Sika MonoTop®-612 N can be applied either manually using traditional techniques or mechanically using wet spray equipment. Thoroughly pre-wet the prepared substrate a recommended 2 hours before application. Keep the surface wet and maintain in SSD condition. The surface shall appear a dark matt appearance without glistening and surface pores and pits shall not contain water.

When manually applying first make a scratch coat by firmly scapping the repair mortar over the substrate surface to form a thin layer and fill any pores or pits in the surface. Ensure the whole surface to be repaired is covered by the scratch coat. Build up layers from bottom to top by pressing mortar well into the repair area. The surface can be finished according to the requirements using a float while wet or with a relevant rough-cast tool as soon as the mortar has started to stiffen.

CURING TREATMENT

Protect the fresh mortar immediately from premature drying using an appropriate curing method e.g. curing compound, moist geotextile membrane, polythene sheet etc.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Australia Pty Limited

ABN 12 001 342 329

aus.sika.com

Tel: 1300 22 33 48

Product Data Sheet

Sika MonoTop®-612 N

April 2023, Version 01.05

020302040030000247

